

Firestone

Nylon 6

Typical Properties

<u>Parameter</u>		<u>C212-15C</u>	
Applications		Wire jacketing	
Colour		Off white	
Heat Stabilized		Yes	
Modified		Yes	
Lubricated		No	
Relative Viscosity	Sulfuric Acid	3.2	
	Formic Acid	82	
Moisture	% Max.	0.08	
Chip Size	mm	2 x 3.5	
Specific Gravity		1.13	ASTM D792
Tensile Strength	MPa	79.2	ASTM D638
	PSI	11,500	
Elongation	%	300	ASTM D412
Flex Modulus	MPa	5,585	ASTM D790
	PSI	375,000	
Flex Strength	MPa	97	ASTM D790
	PSI	14,000	
Notched Izod Impact	ft.lb/in.	0.9	ASTM D256
Deflection Temp.	@ 0.45 MPa / 66 PSI	180°C	ASTM D648
	@ 1.82 MPa / 264 PSI	65°C	
Melt Temperature		220°C	

NON WARRANTY. The information presented in this publication is based upon the research and experience of Firestone and is to the best of its knowledge accurate; however, no guarantee of its accuracy is made. Since Firestone has no control over the conditions under which its products may be employed and since information as to the physiological and other properties of its products is incomplete, Firestone cannot guarantee the results obtained and assumes no liability whatsoever for possible damage or injury whether or not caused by following the suggestions in this brochure. Firestone will not be liable for resulting or consequential damage. Firestone warrants that none of its commercial products infringes the claims of any Canadian or United States patent but no license is granted nor recommendation made hereby to practice any invention covered by any patent owned by Firestone or by others.